

ADLER Acryl-Holzgrund

41001

Water-based primer and intermediate coat for wood in internal and external areas **for DIY and professional use**

PRODUCT DESCRIPTION

General

Water-based, white primer and intermediate coat on a special acrylate-dispersion base. Biocide-free.

Special Properties Testing Standards



- High insulation property for wood extractives and dry water stains.
- High elasticity and body
- Environmentally friendly and odourless
- **French Ordinance DEVL1104875A** regarding the labelling of construction coating products with respect to their emission of volatile pollutants: A+

Areas of application

Wood in internal and external areas.




PROCESSING

Instructions for application



- Please stir the product before use.
- The temperature of the product and object, and the room temperature must be at least 15 C.
- Minor quantities of application and/or stronger dilution will reduce the insulation effect!
- Depending on the species of wood but also on the growing region, the content of the colouring water-soluble wood extractives may vary significantly. It is therefore recommended to test always the coating on a specimen of the original wood in order to judge the insulation effect.
- Overnight drying consolidates the insulation effect.

Application technique

Application method	Using a brush	Roller brush application	Cup gun
Spray nozzle (ø mm)	-	-	1,8 - 2
Spraying pressure (bar)	-	-	2 – 2,5
Thinner	water		
Thinner amount added in %	max. 5		max. 20
Yield per application (m ² /l) ¹⁾	8 - 10		
¹⁾ Yield including addition of thinner and loss while spraying			

Drying times

(at 20 °C room temperature)

Can be sanded	after 3 - 4 hours
Can be recoated	after 3 - 4 hours

Avoid direct sunlight (very quick drying).

Cleaning the tools and equipment

With water immediately after use.

Remove dried-up paint residues with ADLER Abbezier 95125.

SUBSTRATE**Type of substrate**

Wood, wood-based materials

Substrate property (or condition)

The substrate must be dry, clean and capable of holding the paint and it must be free of grease and wax and free from wood dust.

Please observe ÖNORM B 2230 Part 2.

See also VOB, Part C, DIN 18363, paragraph 3; Painting and coating work.

Please observe BFS-data sheet No. 18.

The prerequisite for long storage stability of the coating is compliance with the principles of the constructive wood preservation.

Wood moisture

In case of hardwoods max. 12 % +/- 2 % and for softwoods 15 % +/- 2 %.

Preparation of the substrate

For optimal storage stability, we recommend smooth wooden surfaces are sanded with grain size 80 in the direction of the fibre, cleaned thoroughly and wood extractives such as, for example, resins and resin pockets are removed. Round off any sharp edges.

Clean woods having high resin content and exotic types of woods having constituents that delay the drying process with ADLER Nitroverdünnung 80001.

Treat infestation or attack by algae, moss or fungus with ADLER Fungisan 96349.

Please follow the respective technical data sheets of the products.

COATING SYSTEM

Primer and/or intermediate-coat

Apply 1 coat of Pullex Aqua-Imprägnierung (primer) 51320 ff to protect against blue stain, fungal and insect attack (applies to wood of the durability class according EN 350-2, 3 – 5).

1 - 2 x ADLER Acryl-Holzgrund 41001

Intermediate drying time: approx. 3 - 4 hours
Overnight drying consolidates the insulation effect.

Please follow the respective technical data sheets of the products.

Final coat

1 - 2 x ADLER Glanzacryl 40701

or

1 – 2 x ADLER Seidenacryl 40751

or

1 x Pullex Aqua-Color W10 Weiß (white) 53331

Please follow the respective technical data sheets of the products.

NOTES ON ORDERING

Container sizes

375 ml; 750 ml; 2.5 l

Colour shades

Weiß/white

Supplementary products

ADLER Abbeizer Rote Krähe 95125
ADLER Fungisan 96349
ADLER Seidenacryl 40751
ADLER Glanzacryl 40701
ADLER Nitroverdünnung 80001
Pullex Aqua-Imprägnierung 51320
Pullex Aqua-Color W10 Weiß 53331

OTHER INSTRUCTIONS

Storage stability / Storage



3 years in the original sealed containers.

Store it such that it is protected against moisture, direct sunlight, frost and high temperatures (over 30°C).

Technical Specifications

VOC content EU limit value for ADLER Acryl-Holzgrund (Cat. A/g):
30 gm/l (2010). ADLER Acryl-Holzgrund contains maximum 30 gm/l VOC.

Product code for paints and varnishes

M-GP01

Safety-relevant information



Please follow the associated safety data sheet! The latest version can be retrieved from the Internet at www.adler-lacke.com.

In general, you must avoid inhaling paint aerosols. This is ensured by proper use of a breathing mask (combination filter A2/P2 – EN 141/EN 143).