ADLER Ferroantik



41160

b.w.

i $\downarrow \downarrow \downarrow \downarrow$ +10 °C 6-8 m Water-thinnable matt special-effect paint on the basis of an Product description acrylate emulsion for outdoor and indoor application with very good weathering resistance. Wrought ironwork such as fences, railings, corsses. Field of application Also suitable for refurbishing bonded old coats. For rusty surfaces, we recommend ADLER Ferroblock 41108 (please refer to data sheet). Application Coating, rolling, spraying (Spray nozzle diameter at lest 2 mm!) Zinc/aluminium: Primer 1 x ADLER Acryl-Unigrund 41191 (pleas refer to data sheet) Steel: 2 x ADLER Acryl-Unigrund 41191 Intermediate drying at least 4 hours 2 x ADLER Ferroantik 41160 Topcoat Intermediate drying at least 4 jours The design of the antique look only shows after the second coat. No subsequent brushing necessary! Thinner Water Brushing 5 %, rolling 10 %, spraying 20 % Clean working equipment with water mmediately after use. Working equipment Thoroughly dry spraying devices in order to avoid rusting. Remove dried-on residues with ADLER Abbeizer Rote Krähe 95125 (paint remover). Not below + 10 °C Application and object High air humidity and/or low temperatures tend to delay drying. temperature Repaintable after approx. 3 hours **Drying time** (room temperature 20 °C) 6 - 8 m²/l per coat Spreading rate 375 ml, 750 ml, 2,5 l Packaging Cool but frost-free Storage

09-10 (replaces 02-07) ZKL 4104

ADLER-Werk Lackfabrik, A-6130 Schwaz Fon: 0043/5242/6922-190, Fax: 0043/5242/6922-309, Mail: <u>info@adler-lacke.com</u>

Our instructions are based on the current knowledge and are intended to advise the buyer/user to the best of our knowledge. They must be, however, individually adapted to the application areas and conditions. The buyer/user takes responsibility for the suitability and use of the delivered product. It is therefore recommended to produce a sample specimen for testing the suitability of the product. Otherwise our General Terms of Sale apply. All previous specifications become invalid with this edition. Packaging sizes, colors and available gloss values are subject to change.

Continue

ADLER Ferroantik 41160

Storage stability	3 years in original, sealed containers
Colour	Anthracite
Safety information	Please pay attention tot he safety information sheet! Also when processing low-emission paint, conventional protec- tive measures must be adhered to.