

Innolux Walzgrund

2739

UV roller primer for industrial coating of **furniture and interior finishing**

PRODUCT DESCRIPTION

General


Highly reactive UV-roller primer for water-based, UV-curing pigment varnishes; excellent filling, good grindability, very good permanent elasticity, good insulating effect for MDF panels.

Special properties and standards



- **ÖNORM A 3800-1** (fire behaviour) in conjunction with a flame-retardant substrate: flame-retardant, Q1, Tr 1
- **French ordinance DEVL1104875A** regarding the marking of construction coating products for their emission of volatile pollutants: A+

Application areas



- For the coating of furniture and interior finishing exposed to high levels of stress, such as tabletops and shelves in the kitchen and living area, bathrooms, offices and in the contract sector, fronts and permanently visible areas, surfaces used on seating furniture and not permanently visible areas. Application areas II – IV in accordance with ÖNORM A 1610-12.
- Application in combination with a suitable topcoat system.
- For hardly inflammable or flame-retardant coating systems.

PROCESSING

Instructions for use



- Please stir the product before use.
- The temperature of the product and object, and the room temperature must be at least +15 °C.
- Protect the product from light and sunlight!
- For an optimal surface quality, it is beneficial to apply the primer in 2-3 roller coating steps. Intermediate gelling is recommended if applying more than one coat with a roller.
- Please follow our "**Working guidelines for UV roller paints**".

11-22 (replaces 10-18) ZKL 2739

ADLER-Werk Lackfabrik, A-6130 Schwaz
Phone: 0043/5242/6922-190, Fax: 0043/5242/6922-309, Mail: technical-support@adler-lacke.com

Our instructions for use are based on knowledge available currently and shall guide the buyer/user to the best of one's knowledge, but, however, must be clarified for the areas of application and processing conditions on a case-to-case basis. The buyer/user is responsible for deciding on the suitability and use of the delivered product, which is why it is recommended to produce a sample to check the suitability of the product. Our general terms and conditions of sale are otherwise applicable. All previous data sheets are rendered invalid with the issue of this one. Rights reserved for the modification of the container sizes, colour shades and degrees of gloss available.

Application technique

0-5%

Application method	Rolling
Roller type	Roller coater with reversible dosing roller possibly with grooved roller
Viscosity (sec.) 6-mm-cup, 20 °C	50 ± 10 s
Application quantity (g/m ²)	approx. 20 - 30 g/m ² per application; Total application quantity primer: max. 90 g/m ²

The product is ready to use.

The shape and properties of the substrate affect the consumption/yield. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying conditions

Immediate **UV-curing** without flashing off previously:

	Feed	
	Intermediate gelling	Curing
Hg radiator 80 W/cm	10 - 14 m/min	5 - 7 m/min
Hg radiator 120 W/cm	12 - 16 m/min	7 - 10 m/min

Cleaning the working equipment

With Wasch-Verdünnung 80072 immediately after use.

SUBSTRATE**Type of substrate**

Hard and softwood (solid wood, veneer, (coated) chipboard, wood fibre boards), carrier plates coated with priming film.

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

Preparation of the substrate

Calibration grinding

Hardwoods: wood sanding grit size 150–180

Softwoods: wood sanding grit size 120–150

MDF panels: cleaning sanding grain size 180 - 220

COATING SYSTEM**Primer**

50 - 60 g/m² Innolux Walzgrund 2739000200, depending on the required body

Example:

1 x 25 - 30 g/m²

Intermediate gelling with 1 Hg radiator 80 W/cm, feed rate 10 m/min

1 x 25 g/m²

Curing with 2 Hg radiator 80 W/cm, feed rate 10 m/min

Intermediate sanding

Grit size 320 - 400

Intermediate sanding must be carried out immediately before the subsequent coating is applied in order to ensure good intermediate adhesion. Avoid sanding straight through!

Topcoat

Innolux Floor Decklack 2766 in the desired degree of gloss

or

1 x 120 g/m³ ADLER Pigmolux DC 29301 ff in the desired colour shade

Please refer to the relative technical data sheets of the products.

CLEANING & MAINTENANCE**Cleaning and maintenance**

Cleaning with Clean Möbelreiniger 96490. Maintenance with Clean-Möbelpflege Plus 7222000210.

Please refer to the relative technical data sheets of the products.

ORDERING INFORMATION**Size of trading unit**


25 kg

Delivery qualities

Innolux Walzgrund 2739000200

Supplementary products

Innolux Verdünnung LM 80075
Wasch-Verdünnung 80072
Clean-Möbelreiniger 96490
Clean-Möbelpflege Plus 7222000210

FURHTER DETAILS**Durability / storage**

At least 9 months in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Technical specifications

Delivery viscosity	50 ± 5 s according to DIN 53211 (6-mm-cup, 20°C)
--------------------	--

Safety-related information

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.

The product is only suitable for industrial use.